

CORROSION-RESISTANT STEELS - FERRITIC-AUSTENITIC (DUPLEX) STEELS

Application Segments

Oil & Gas/CPI

Available Product Variants

Long Products*

Semi-Finished Products / Billet

Plates

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Product Description

BÖHLER A911SA is a ferritic-austenitic stainless steel of Type 25%Cr with PREN of min. 40. It offers excellent corrosion resistance against general corrosion, stress corrosion cracking, corrosion fatigue, pitting, crevice and erosion corrosion and possessing very high mechanical strength properties. However, it contains less copper compared to other super Duplex SS but a deliberate addition of tungsten instead, claimed to selectively improve corrosion resistance. Good weldability, post weld heat treatment not necessary.
Max. temperature for long periods of service: 280°C (535°F) / (300°C/570°F possible for short periods).

Surface condition for optimum corrosion resistance: pickled or machined.

Components in offshore, waste water, sea water desalination and chemical plants with aggressive chloride-containing media e.g. heat exchangers, separator parts, compressor and pump components, turbine blades.

Process Melting

Airmelted

Applications

- > Components for Chemical plants (incl. LNG, FGD, Urea, LDPE, etc.)
- > CPI (incl. LNG, Urea)
- > Food processing industry
- > Pumps and High Pressure Components
- > Well Completion Tools
- > Oil & Gas, CPI & Renewables
- > Components for the recycling industry
- > Fasteners, Bolts, Nuts
- > Oil & Gas / CPI
- > Tubular Products, Flanges, Fittings
- > Wellhead, X-mas trees and Manifolds (incl. Tubing hangers), BOPs
- > Well Logging Tools
- > Components for food processing and animal feed
- > Flowlines & Connectors
- > Other Oil and Gas + CPI components
- > Valves and Actuators
- > Chemical industry - general
- > Drilling tools and components

Technical data

| Material designation | | Standards | |
|----------------------|--------------|------------|--------|
| F55 | Market grade | 10088-3 | EN ISO |
| 1.4501 | SEL | A182/A182M | ASTM |
| X2CrNiMoNCuW25-7-4 | EN | A276/A276M | |
| S32760 | UNS | A479/A479M | |
| | | MDS D57 | NORSOK |

Chemical composition (wt. %)

| C | Si | Mn | P | S | Cr | Mo | Ni | W | Cu | N |
|------------|-----------|-----------|------------|------------|--------------|------------|------------|--------------|--------------|--------------|
| max. 0.030 | max. 1.00 | max. 1.00 | max. 0.030 | max. 0.010 | 24.0 to 26.0 | 3.0 to 4.0 | 6.0 to 8.0 | 0.50 to 1.00 | 0.50 to 1.00 | 0.20 to 0.30 |

Refers to NORSOK MDS D57-UNS 32760 | PREN = % Cr + 3.3 x % Mo + 16 x % N min 40.

Delivery condition

Solution Annealed + Quenched

| | |
|------------------------|--|
| Hardness (HB) | max. 310 hot finished or cold finished |
| Tensile Strength (MPa) | min. 750 hot finished or cold finished |
| Yield Strength (MPa) | min. 550 hot finished or cold finished |

Round Bars and Wire Rod (if any)

| Diameter* | | mm | |
|---------------|---|--------|--|
| ROLLED | | | |
| 5.00 | - | 13.50 | |
| 12.50 | - | 130.00 | |
| FORGED | | | |
| 131.10 | - | 200.00 | |

* Diameter 5.00 - 13.50 mm available as Wire Rod.

Diameter 12.5 - 130 mm round bars.

More information regarding MOQ, lengths and tolerances upon request. Flat bars on request.

Long Products: For additional specifications, technical requirements, and other dimensions, please contact our regional voestalpine BÖHLER sales companies.

Sheet & Plates: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact voestalpine BÖHLER Bleche GmbH & Co KG.

Semi-Finished Products: Product Variant may differ in terms of melting process, technical data, delivery, and surface condition as well as available product dimensions. Please contact the business unit Semi Finished Products of voestalpine BÖHLER Edelstahl GmbH & Co KG.

The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@boehler-edelstahl.at

<https://www.voestalpine.com/boehler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.